

## Technical Data Sheet

**Type:** ESTANE<sup>®</sup> ECO 12T95 is an aromatic high performance natural-based polyester Thermoplastic Polyurethane (TPU)

**Features:** Properties similar to standard TPU of same hardness; excellent mechanical properties and abrasion resistance

**Uses:** Injection molding

Physical Properties	Value (Metric)	Unit	Test Method
Hardness (5 sec)	95±3	Shore A	ISO 868
Specific Gravity	1.17	g/cm <sup>3</sup>	ISO 2781
Tensile Strength	36	MPa	ISO 37
Ultimate Elongation	415	%	
Tensile Stress at:			
- 100 % Elongation	12	MPa	ISO 37
- 300 % Elongation	28	MPa	
Tear Strength			
Graves	142	kN/m	ISO 34B
Abrasion resistance	28	mm <sup>3</sup>	ISO4649
Bio-based content	32	%	ASTM D6866-12

**Remark:**

- Prior to testing samples were conditioned at 23°C for 48 hours
- Listed values are 'typical (average) values' and should/cannot be applied for specification purposes

## Supply Form and Standard Packaging

- ESTANE<sup>®</sup> ECO 12T95 is supplied in pellet form and packaged in 25kg bags.

## Material Preparation

- Prior to processing, ESTANE<sup>®</sup> ECO 12T95 must be dried at **190~220°F (88~104°C)** for 2-4 hours.
- It is recommended to dry the material in a desiccant type dryer. Target dew point should be **-40°C**.
- Depending on the applied processing technique, the maximum moisture level should be 0.02%.

## Material Preparation

- ESTANE<sup>®</sup> ECO 12T95 is injection molded on any conventional molding machine equipped with general purpose screw.
- Typical screw L/D ratio lies between 18 and 23; the optimum compression ratio falls between 2:1 and 2.5:1.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.



**Recommended Starting INJECTION MOLDING Temperature Profile:**

	°C
<b>Feed zone</b>	<b>40</b>
<b>Zone 1</b>	<b>210</b>
<b>Zone 2</b>	<b>215</b>
<b>Zone 3</b>	<b>220</b>
<b>Zone 4</b>	<b>220</b>
<b>Nozzle</b>	<b>225</b>

**For further information refer to Lubrizol Advanced Materials processing guides.**

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2022 The Lubrizol Corporation.  
All rights reserved. All marks are the property of The Lubrizol Corporation.



<http://go.lubrizol.com/EP>